

# Technical data sheet:

## SIGA-Rissan®

**Updated on:** 11/12/2012

**Distributor:** SIGA Cover, Inc.

**Type of application:** durably airtight joints and penetrations in vapor control layers and wood-based panels

**Instructions for application:** see Manual

**Construction:** reinforced PE film, elastic, green transparent, with SIGA acrylic pressure sensitive adhesive

**Packaging unit:**

Rissan 60	10 rolls / box
Rissan 100	6 rolls / box
Rissan 150	4 rolls / box

### Characteristics:

			Standards	Units	Values
Dimensions		Length / width	Rissan 60	m / m feet / inch	25 / 0.06 82 / 2.4
			Rissan 100	m / m feet / inch	25 / 0.10 82 / 3.9
			Rissan 150	m / m feet / inch	25 / 0.15 82 / 5.9
Temperature resistance				°F °C	- 40 °F to + 212 °F - 40 °C to + 100 °C
Processing temperature				°F °C	from + 14 °F from - 10 °C
Water vapor transmission:			ASTM E-96A	US perm	0.09
Water resistance			AATCC-127	cm	500
Ageing resistance			high permanent adhesive strength, non-drying and non-embrittling since without caoutchouc, resin or solvent, can reliably and durably follow structural movements		
Suitability for storage			unlimited store in a cool, dry place in its original box		